

08-03-00

A

UTILITY PATENT APPLICATION TRANSMITTAL <small>(Only for new nonprovisional applications under 37 CFR 1.53(b))</small> ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20231	Attorney Docket No.	71111
	First Named Inventor or Application Identifier	Linda Gail Bernard
	Express Mail Label No.	EE618007575US
	Total Pages	1

Jc887 U.S. PTO

09/630517

08/02/00

1. <input checked="" type="checkbox"/> Specification [Total Pages 34] 2. <input checked="" type="checkbox"/> Drawing(s) (35 USC 113) [Total Sheets 2] 3. Oath or Declaration [Total Pages] a. <input type="checkbox"/> Newly executed (original or copy) b. <input type="checkbox"/> Copy from a prior application (37CFR 1.63(d)) (for continuation/divisional with Box 9 completed) [Note Box 4 below] i. <input type="checkbox"/> DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37CFR 1.63(d)(2) and 1.33(b). 4. <input type="checkbox"/> Incorporation By Reference (useable if Box 3b is checked) The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 3b, is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein. 5. <input type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input type="checkbox"/> Copies of IDS Citations	6. <input type="checkbox"/> Preliminary Amendment 7. <input checked="" type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized) 8. <input type="checkbox"/> Other: 9. This application is a: <input type="checkbox"/> Continuation <input type="checkbox"/> Divisional <input type="checkbox"/> Continuation-in-part (CIP) of Prior application No: _____ <input type="checkbox"/> Amend the specification by inserting before the first line ---This is a application of copending application Serial No. filed <input type="checkbox"/> An associate power of attorney appears in the prior application. A copy is enclosed. <input type="checkbox"/> Cancel in this application original claims of the prior application before calculating the filing fee (At least one original independent claim must be retained for filling purposes).
---	--

CLAIMS	(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA	(4) RATE	(5) CALCULATIONS
TOTAL CLAIMS (37 CFR 1.16(c))		29 - 20 =	9	X \$18 =	162
INDEPENDENT CLAIMS (37 CFR 1.16(b))		2 - 3 =	0	X \$78 =	0
MULTIPLE DEPENDENT CLAIMS (if applicable) (37 CFR 1.16(d))				+ \$260 =	0
				BASIC FEE (37 CFR 1.18(a))	690
TOTAL to be CHARGED =					\$ 852

The Commissioner is hereby authorized to charge any additional fees under 37 CFR 1.16 and 1.17 which may be required by this paper or credit any overpayment to Deposit Account No. 05-0221. Any submission during prosecution which requires an EOT should be treated as including a Petition for the required extension and be charged to Deposit Account No. 05-0221. A duplicate copy of this sheet is enclosed.

CORRESPONDENCE ADDRESS	
NAME Karen A. Harding	SIGNATURE <i>Karen A. Harding</i>
ADDRESS Eastman Chemical Company P.O. Box 511 Kingsport, Tennessee 37662-5075	DATE <i>Aug 2, 2000</i>
REGISTRATION NUMBER: 33,967	PHONE: (423) 229-4016
FAX: (423) 229-1239	

CERTIFICATE OF MAILING UNDER 37 CFR 1.10	
"EXPRESS MAIL" Mailing Label No.: EE618007575US	Date of Deposit: <i>August 2, 2000</i>
I hereby certify that this Utility Patent Transmittal and the Documents referred to as being enclosed therein are being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner for Patents, Washington, D.C. 20231.	
<i>Jo Ann White</i> Jo Ann White	

INVENTOR INFORMATION

Inventor One Given Name:: Linda Gail

Family Name:: Bernard

Postal Address Line One:: 309 Castaway Drive

City:: Kingsport

State or Province:: TN

Country:: USA

Postal or Zip Code:: 37663-3568

City of Residence:: Kingsport

State or Province of Residence:: TN

Country of Residence:: USA

Citizenship Country:: USA

Inventor Two Given Name:: Horst

Family Name:: Clauberg

Postal Address Line One:: 2601 J B Dennis #210

City:: Kingsport

State or Province:: TN

Country:: USA

Postal or Zip Code:: 37660-4786

City of Residence:: Kingsport

State or Province of Residence:: TN

Country of Residence:: USA

Citizenship Country:: USA

Inventor Three Given Name:: Michael John

Family Name:: Cyr

Postal Address Line One:: 204 Coralwood Drive

City:: Kingsport

State or Province:: TN

Country:: USA

Postal or Zip Code:: 37663-2712

City of Residence:: Kingsport

State or Province of Residence:: TN

Country of Residence:: USA

Citizenship Country:: USA

Inventor Four Given Name:: John Walker

Family Name:: Gilmer

Postal Address Line One:: 2624 Wildwood Drive

City:: Kingsport

State or Province:: TN

Country:: USA

Postal or Zip Code:: 37660-4754

City of Residence:: Kingsport

State or Province of Residence:: TN

Country of Residence:: USA

Citizenship Country:: USA

Inventor Five Given Name:: James Christopher

Family Name:: Matayabas, Jr.

Postal Address Line One:: 1380 West Saragosa Place

City:: Chandler

State or Province:: AZ
Country:: USA
Postal or Zip Code:: 85224-7216
City of Residence:: Chandler
State or Province of Residence:: AZ
Country of Residence:: USA
Citizenship Country:: USA
Inventor Six Given Name:: Jeffrey Todd
Family Name:: Owens
Postal Address Line One:: 117 Willowbrook Drive
City:: Kingsport
State or Province:: TN
Country:: USA
Postal or Zip Code:: 37660-7581
City of Residence:: Kingsport
State or Province of Residence:: TN
Country of Residence:: USA
Citizenship Country:: USA
Inventor Seven Given Name:: Mark Edward
Family Name:: Stewart
Postal Address Line One:: 1104 Dover Drive
City:: Kingsport
State or Province:: TN
Country:: USA
Postal or Zip Code:: 37664
City of Residence:: Kingsport
State or Province of Residence:: TN
Country of Residence:: USA
Citizenship Country:: USA
Inventor Eight Given Name:: Sam Richard
Family Name:: Turner
Postal Address Line One:: 1037 Sussex Drive
City:: Kingsport
State or Province:: TN
Country:: USA
Postal or Zip Code:: 37660-5836
City of Residence:: Kingsport
State or Province of Residence:: TN
Country of Residence:: USA
Citizenship Country:: USA
Inventor Nine Given Name:: Shriram
Family Name:: Bagrodia
Postal Address Line One:: 2649 Suffolk Street
City:: Kingsport
State or Province:: TN
Country:: USA
Postal or Zip Code:: 37660-5803
City of Residence:: Kingsport
State or Province of Residence:: TN
Country of Residence:: USA

Citizenship Country:: USA

CORRESPONDENCE INFORMATION

Name Line One:: Karen A. Harding
Address Line One:: Eastman Chemical Company
Address Line Two:: P.O. Box 511
City:: Kingsport
State or Province:: TN
Country:: USA
Postal or Zip Code:: 37662-5075
Telephone One:: (423) 229-4016
Fax One:: (423) 229-1239
Electronic Mail One:: kahardin@eastman.com

APPLICATION INFORMATION

Title Line One:: POLYAMIDE NANOCOMPOSITES WITH OXYGEN SCA
Title Line Two:: VENGING CAPABILITY
Total Drawing Sheets:: 1
Formal Drawings?: Yes
Application Type:: Utility
Docket Number:: 71111
Secrecy Order in Parent Appl.?: No

REPRESENTATIVE INFORMATION

Registration Number One:: 33967
Registration Number Two:: 35424
Registration Number Three:: 37096
Registration Number Four:: 33864
Registration Number Five:: 29000
Registration Number Six:: 35366
Registration Number Seven:: 38346
Registration Number Eight:: 39076

CONTINUITY INFORMATION

This application is a:: NON PROV. OF PROVISIONAL
> Application One:: 60/148,138
Filing Date:: 08-10-1999

This application is a:: NON PROV. OF PROVISIONAL
> Application Two:: 60/165,064
Filing Date:: 11-12-1999

Source:: PrintEFS Version 1.0.1

POLYAMIDE NANOCOMPOSITES WITH OXYGEN SCAVENGING CAPABILITY

Cross Reference to Related Applications

- 5 This application claims the benefit of United States Provisional Application Serial No. 60/165,064 filed November 12, 1999 and 60/148,138, filed August 10, 1999.

Background of Invention

- 10 MXD6 is a commercially available partially-aromatic nylon prepared from adipic acid and meta-xylene diamine, and is also available as a copolyamide with comonomers including isophthalic acid. MXD6 and copolyamides are preferred barrier materials for use in multilayer PET bottles due to their similar processing conditions and rheology to PET and due to their improved resistance to
- 15 delamination from PET compared to EVOH. However, their use is limited because bottles comprising MXD6 as a blend or as one or more discrete layers with, for example, PET have insufficient barrier for packaging highly oxygen sensitive food and/or are not recyclable in processes established for mono-layer PET bottles due to the large amount of MXD6 that is required.

- 20 Platelet particles have been incorporated to improve the passive oxygen barrier of MXD6; however, relatively large amounts of the MXD6-platelet particle composite are still needed to achieve the desired oxygen barrier and, therefore, the bottles are still difficult, if not impossible to recycle.

- Certain transition metal catalysts have been added to MXD6 to impart
- 25 oxygen scavenging capability (active barrier), which greatly reduces the amount of MXD6 needed. However, most food and beverage products require high gas barrier properties to more than just oxygen. For example, beer bottles require high oxygen barrier to protect the beer and require high carbon dioxide barrier to contain the desired carbon dioxide within the package. Active scavenger approaches often
- 30 fall short of meeting the barrier requirements other than or require the use of such a

large amount of oxygen scavenging MXD6 that the bottles are difficult or impossible to recycle.

Prior Art

5 U.S. patent 4,739,007 discloses composite materials comprising a polyamide matrix and a dispersed layered silicate material that is incorporated during polymerization and imparts high mechanical strength and excellent high temperature properties.

10 U.S. patent 4,810,734 discloses nylon composites comprising a layered silicate material that has been treated with certain organic ammonium compounds and incorporated by synthesis using a dispersing aid.

15 PCT application WO 93/04117 discloses composite materials comprising a polyamide matrix and a layered silicate material that has been modified with certain primary or secondary organic ammonium compounds incorporated during melt extrusion to impart improved modulus to the polymer composite.

PCT application WO 93/11190 discloses nylon composites comprising a layered silicate material that has been treated first with certain organic ammonium compounds then with certain silane compounds and incorporated by melt blending.

20 US 97/24103 discloses polymer composites comprising a layered silicate material that has been treated first with certain organic ammonium compounds then with an expanding agent and incorporated by synthesis or by melt blending.

25 U.S. patents 5,021,515 and 5,034,252 disclose high barrier containers comprising mixtures of PET and nylon comprising a transition metal oxygen scavenging catalyst. US patent 5,077,111 discloses recyclable multilayer preforms and bottles comprising a total of 1-8 wt% of MXD6 comprising a cobalt salt that catalyzes oxygen scavenging. This patent suggests that when the total content of MXD6 is less than or equal to the preferred amount of 4 wt% that the bottles are recyclable. In practice, however, it has been found that bottles comprising less than
30 preferred barrier requirements for packaging products that require high gas barrier

to oxygen plus one or more other gasses, such as beer. Beer brewing companies have published their preferred gas barrier requirements – see for example Norm Nieder “Is Plastic Ready for Beer,” Proceeding of the 3rd International Conference on Rigid Polyester Packaging Innovations for Food and Beverages, NovaPak Americas ’98. Those requirements include less than 10% loss of carbon dioxide from 2.8-3.0 volumes for about 105-120 days. Bottles prepared as described in the above US patents must comprise more than about 4.5 wt% MXD6 to meet this requirement. Because such large amounts of MXD6 are required, true recyclability is problematical and/or the preferred gas barrier properties are not achieved, which restricts the applications to short term use, such as promotional and stadium events.

Description of the Invention

This invention relates to polymer-platelet particle composites composed of at least one polymer resin and platelet particles uniformly dispersed therein and products produced from said composite. More specifically, this invention relates to a polymer-platelet particle composite comprised of at least one polyamide resin, at least one oxygen scavenging catalyst, and at least one layered silicate material. Typically, the layered silicate material is treated to enhance dispersibility into the composite. The present invention further relates to a process for forming polymer-platelet particle composites comprising mixing the oxygen scavenging catalyst with the layered silicate material and organic cation to bind the organic cation and oxygen scavenging catalyst to said layered silicate material to form an organoclay and incorporating the organoclay into a polymer. The polymer-platelet particle composites produced according to the present invention are especially useful for preparing clear bottles and film that are recyclable, exhibit improved active gas barrier properties to oxygen, and exhibit improved passive barrier to other gasses. By virtue of their high gas barrier properties, polymer-platelet particle composites produced according to the present invention can be used in relatively minor amounts as either a blend or a very thin layer with PET and related copolymers, either virgin or post consumer recycled, and this low concentration of polymer-

platelet particle composite provides the unique combination of good oxygen gas barrier protection, good carbon dioxide barrier retention, and recyclability.

Platelet Particles

5 The polymer-platelet particle composites of the present invention comprise up to about 30 weight percent, preferably less than about 20 weight percent, of certain platelet particles derived from at least one layered silicate material which has been modified with at least one ammonium compound. The amount of platelet particles is determined by measuring the residual ash of the polymer-platelet
10 particle compositions when treated in accordance with ASTM D5630-94, which is incorporated herein by reference. The gas barrier improvement increases with increasing concentration of platelet particles in the composite. While amounts of platelet particles as low as about 0.01 percent provide improved barrier (especially when well dispersed and ordered), compositions having at least about 0.5 weight
15 percent of the platelet particles are preferred because they display desirable improvements in gas permeability.

 Preferred layered silicate materials employed in the invention include any solid material having at least some inorganic anionic atoms, ions, or chemical groups arranged in generally planar layers in the solid state, wherein the spacing
20 between at least some of the generally planar layers are capable of being increased, swelled, or separated by the insertion of inorganic or organic materials there between. Generally layered silicate materials are a dense agglomeration of platelet particles which are closely stacked together like cards. The platelet particles of the present invention have a thickness of less than about 2 nm and a diameter in the
25 range of about 10 to about 5000 nm. For the purposes of this invention, such measurements refer only to the platelet particle and not to the ammonium compounds or any additional dispersing aids and treatment compounds which might be used. Suitable layered silicate material are free flowing powders having a cation exchange capacity between about 0.3 and about 3 meq/g and preferably

between about 0.8 and about 1.5 meq/g and more preferably from about 0.95 to about 1.25 meq/g.

Many layered silicate materials are silicates. As used herein, "silicate" shall mean any composition having silicon atoms bound to one or more oxygen atoms to form anionic groups, in combination with one or more additional cations, wherein the cations may be inorganic, metallic, or organic cations.

Examples of suitable layered silicate materials include natural, synthetic and modified phyllosilicates. Illustrative of such natural clays are smectite clays, such as montmorillonite, hectorite, mica, vermiculite, bentonite, nontronite, beidelite, volkonskoite, saponite, sauconite, magadite, kenyaite and the like. Illustrative of such synthetic clays are synthetic mica, synthetic saponite, synthetic hectorite, and the like. Illustrative of such modified clays are flourinated montmorillonite, flourinated mica, and the like. Suitable layered silicate materials are available from various companies including Southern Clay Products, Gonzalez, Texas; Nanocor, Inc, Arlington Heights, Illinois; Kunimine Industries, Ltd., Chiyodaku, Tokyo, Japan and Rheox of Hightown, New York . The most preferred platelet particles are derived from sodium bentonite or sodium montmorillonite. One of ordinary skill in the art will readily recognize that Wyoming type montmorillonite and/or Wyoming-type bentonite are naturally occurring layered silicate materials comprising large proportions of sodium bentonite or sodium montmorillonite. Thus it may be stated that highly preferred platelet particles for use in the present invention are residues derived from further treatment of any of sodium bentonite, sodium montmorillonite, "Wyoming type" bentonite or "Wyoming type" montmorillonite. It is to be understood that at least some of the sodium cations of a natural or synthetic sodium bentonite or sodium bentonite , a naturally occurring "Wyoming type" bentonite or "Wyoming type" montmorillonite are removed and/or exchanged when treated with salts of the alkoxylated onium cations of the invention. Nevertheless, for the purposes of this invention and disclosure, the residues of the treated clays may be referred to, and are defined as a "Wyoming type bentonite", a "Wyoming type montmorillonite", a "sodium

bentonite", or a "sodium montmorillonite". Residues of such clays need not contain detectable amounts of sodium after the clays have undergone treatment with the alkoxylated onium cation salts of the invention. However, some sodium cations may remain. Such clays are readily available in the U.S., known as
5 Wyoming type montmorillonite, and other parts of the world, including the Kunipia clays available from Kunimine Industries, Inc.

Preferred layered silicate materials are phyllosilicates of the 2:1 type having a cation exchange capacity of 0.5 to 2.0 meq/g. The most preferred layered silicate materials are smectite clay minerals, particularly bentonite or montmorillonite,
10 more particularly Wyoming-type sodium montmorillonite or Wyoming-type sodium bentonite having a cation exchange capacity from about 0.95 to about 1.25 meq/g. The most preferred layered silicate materials are derived from sodium bentonite or sodium montmorillonite.

Other non-clay materials having the above-described ion-exchange capacity and size, such as chalcogens, may also be used as a source of platelet particles
15 under the present invention. Chalcogens are salts of a heavy metal and group VIA (O, S, Se, and Te). These materials are known in the art and do not need to be described in detail here.

The layered silicate materials are typically treated to improve dispersion
20 into the composite. Many useful clay treatments are known in the art, and these treatments may also be used before, after, or during incorporation of the layered silicate materials into the composites of this invention without deviating from the scope of this invention. Examples of useful treatments include, but are not limited to treatments with silane compounds, expanding agents, polymers and oligomers,
25 dispersing aids, organic cation salts, and their combinations.


Examples of useful treatment with silane compounds include those treatments disclosed in WO 93/11190, incorporated herein by reference. Examples of useful silane compounds includes (3-glycidoxypropyl)trimethoxysilane, 2-methoxy (polyethyleneoxy)propyl heptamethyl trisiloxane, octadecyl dimethyl (3-
30 trimethoxysilylpropyl) ammonium chloride and the like.

Examples of useful treatment with expanding agents include those treatments disclosed in US 97/24103, incorporated herein by reference. Oligomeric polymers may also be used as suitable expanding agents.

Useful polymers and oligomers for treating clays include those disclosed in
 5 US patents 5,552,469 and 5,578,672, incorporated herein by reference.

Many dispersing aids are known, covering a wide range of materials including water, alcohols, ketones, aldehydes, chlorinated solvents, hydrocarbon solvents, aromatic solvents, and the like or combinations thereof.

Useful organic cation salts for additional treatment can be represented as
 10 follows:




wherein M represents nitrogen or phosphorous; X^- represents an anion, preferably a
 20 halide atom such as chloride or bromide; R_1 , R_2 , R_3 and R_4 are independently selected from organic and oligomeric ligands having 1 to 30 carbon atoms or may be hydrogen.

Examples of useful organic ligands include, but are not limited to, linear or branched alkyl groups having 1 to 22 carbon atoms, aralkyl groups which are
 25 benzyl and substituted benzyl moieties including fused-ring moieties having linear chains or branches of 1 to 100 carbon atoms in the alkyl portion of the structure, aryl groups such as phenyl and substituted phenyl including fused-ring aromatic substituents, beta, gamma unsaturated groups having six or less carbon atoms, and alkyleneoxide groups having repeating units comprising 2 to 6 carbon atoms.

30 Examples of useful oligomeric ligands include, but are not limited to a poly(alkylene oxide) group such as polyethylene glycol groups, and polybutylene glycol groups; polystyrene, polyacrylate, polycaprolactone, and the like.


Useful alkoxyated ammonium compounds for the process of this invention may also include mono-alkoxyated, di-alkoxyated, tri-alkoxyated, and tetra-alkoxyated ammonium compounds. Examples of useful alkoxy ligands include, but are not limited to, hydroxyethyl, hydroxypropyl, hydroxybutyl, poly(ethylene oxide), poly(propylene oxide), poly(butylene oxide), and the like.

Illustrative of suitable mono-alkoxyated amine compounds, which are converted to the ammonium salt by reaction with a Brønsted acid, include, but are not limited to, compounds represented as follows:




wherein N represents nitrogen; X^- represents an anion, which is preferably a halide atom such as chloride or bromide; R_1 , R_2 , and R_3 may be the same or different and are organic or oligomeric ligands comprising 1 to 30 carbon atoms, or may be hydrogen; n is at least 1; R_4 is hydrogen or a hydrocarbon comprising 1 to 4 carbon atoms; and R_5 is hydrogen or a hydrocarbon comprising 1 to 7 carbon atoms.

With respect to the alkoxyated onium compounds or cations, preferred alkoxy groups comprise a group or residue exemplified above and below by the formula:



which may represent either an alkoxyl group or a hydroxyalkyl group. Examples of useful alkoxyl ligands include, but are not limited to groups or residues that comprise methoxymethyl, hydroxyethyl, methoxyethyl, hydroxypropyl, hydroxybutyl, poly(ethylene oxide), poly(propylene oxide), poly(butylene oxide), and the like. Preferred mono-alkoxylated ammonium cations are tertiary (*i.e.* only one of R_1 , R_2 or R_3 are hydrogen) or are quaternary (*i.e.* none of R_1 , R_2 or R_3 are hydrogen) and are sold under the trade name of Jeffamine by Huntsman.

Examples of useful di-alkoxylated ammonium compounds include, the compositions represented as follows:




wherein N represents nitrogen; X^- represents an anion which is preferably a halide atom such as chloride or bromide; R_1 and R_2 may be the same or different and are organic or oligomeric ligands comprising 1 to 30 carbon atoms, or may be hydrogen; p and n are at least 1 and can be the same or different; and R_3 , R_4 , R_5 and R_6 may be same or different and are hydrogen or hydrocarbons comprising 1 to 4 carbon atoms. Examples of useful di-alkoxylated ammonium cations include, but are not limited to bis(1-hydroxymethyl), octadecyl ammonium (having a hydrogen attached to nitrogen); bis(2-hydroxyethyl), octadecyl methyl ammonium; octadecyl isopropoxy dimethyl ammonium; and the like or a mixture thereof.

Illustrative examples of suitable di-ethoxylated ammonium salts include those available under the trade name Ethoquad or Ethomeen from Akzo Chemie America, namely, Ethoquad 18/25 which is octadecyl

methylbis(polyoxyethylene[15]) ammonium chloride and Ethomeen 18/25 which is octadecyl bis(polyoxyethylene[15]) amine, wherein the numbers in brackets refer to the total number of ethylene oxide units.

5 Preferably, R_1 and R_2 are organic ligands. Preferred di-alkoxylated ammonium cations are tertiary (*i.e.* only one of R_1 or R_2 are hydrogen) or are quaternary (*i.e.* neither R_1 or R_2 are hydrogen). Preferred di-alkoxylated ammonium cations within this class have at least one hydroxyalkyl residue (*i.e.* at least one of R_5 or R_6 are hydrogen). Even more preferred di-alkoxylated ammonium cations within this class are tertiary or quaternary, and have two hydroxyalkyl ligands (*i.e.* R_1 and R_2 are not hydrogen, and R_5 and R_6 are hydrogen).

Useful tri-alkoxylated ammonium salts for the compositions, nanocomposites, and processes of this invention can be represented as follows:




15

wherein N represents nitrogen; X^- represents an anion which is preferably a halide such as chloride or bromide; R_1 is an organic or oligomeric ligand comprising 1 to 30 carbon atoms, or may be hydrogen; n, p, and q are at least 1 and can be the same or different; and R_2 , R_3 , R_4 , R_5 , R_6 and R_7 may be the same or different and are hydrocarbons comprising 1 to 4 carbon atoms or hydrogen. Preferably, R_1 and R_2 are not oligomeric. One of ordinary skill in the art will recognize that tri-alkoxylated ammonium salts are inherently at least tertiary, and will be quaternary if R_1 is not hydrogen.


20

Useful tetra-alkoxylated ammonium salts for the nanocomposite and process of this invention can be represented as follows:



5 wherein N represents nitrogen; X^- represents an anion which is preferably a halide atom such as chloride or bromide; m, n, p, and q are at least 1 and can be the same or different; and R_1 , R_2 , R_3 , R_4 , R_5 , R_6 , R_7 and R_8 may be the same or different and are hydrocarbons comprising 1 to 4 carbon atoms or hydrogen.

Certain preferred alkoxylated ammonium salts for the compositions, nanocomposites and process of this invention is a di-ethoxylated ammonium salt
10 represented as follows:



15 wherein N represents nitrogen; X^- represents an anion which is preferably a halide atom such as chloride or bromide; R_1 is an organic or oligomeric ligand comprising at least 8 carbon atoms; R_2 is hydrogen or an organic and oligomeric ligand comprising at least 8 carbon atoms; and p and n are at least 1 and can be the same or different. Preferably, R_1 and R_2 are not oligomeric. Preferably, only one of R_1 and R_2 is hydrogen (*i.e.* the cation is tertiary), or neither R_1 or R_2 is hydrogen (*i.e.* the cation is quaternary).

Even more preferably, N represents nitrogen; R₁ is an organic ligand comprising from 1 to 30 carbon atoms; R₂ is hydrogen or an organic ligand from 1 to 4 carbon atoms; and p and n are at least 1 and can be the same or different. Particularly preferably, R₂ is an organic ligand (i.e. the cation is quaternary).

5 Illustrative examples of suitable di-ethoxylated ammonium salts include those available under the trade name ETHOQUAD or ETHOMEEN from Akzo Chemie America, Chicago Illinois, namely, ETHOQUAD 18/25, which is octadecyl methyl bis(polyoxyethylene[15]) ammonium chloride and ETHOMEEN 18/25, which is octadecyl bis(polyoxyethylene[15])amine, wherein the numbers in
10 brackets refer to the total number of ethylene oxide units. The most preferred alkoxylated ammonium cations are octadecyl methyl bis(2-hydroxyethyl) ammonium and methyl bis(2-hydroxyethyl) tallow ammonium.

One of ordinary skill in the art will recognize that tallow is a mixture of materials derived from the treatment of animal fats, principally comprising a 50%
15 majority mixture of chemical compounds having saturated and unsaturated C₁₈ alkyl groups also comprising smaller amounts of other alkyl groups, including C₁₆ alkyl groups. Tallow may be treated to remove any unsaturated groups, to generate hydrogenated tallow. It is to be understood that a reference to "tallow" includes "hydrogenated tallow" unless otherwise specifically indicated herein.

20 Numerous methods to modify layered silicate materials with ammonium compounds are known, and any of these methods may be used in the process of this invention. One embodiment of this invention is the modification of at least one layered silicate material with at least one ammonium compound by the process of dispersing the layered silicate material(s) in hot water, most preferably from about
25 50 to about 80°C, adding (neat or dissolved in water or alcohol) an organic ammonium salt or an organic amine and a Brønsted acid (thereby forming the organic ammonium salt in situ) or their combinations and mixtures with agitation. Then the mixture is blended for a period of time sufficient for the organic ammonium cations to exchange most of the metal cations present in the galleries
30 between the layers of the clay material. Then, the organically modified layered

silicate material (organoclay) is isolated by methods known in the art including, but not limited to, filtration, centrifugation, spray drying, and their combinations. It is desirable to use a sufficient amount of the organic ammonium salt to permit exchange of most of the metal cations in the galleries of the layered particle for organic cations; therefore, at least about 0.5 equivalent of organic cation salt is used and up to about 3 equivalents of organic cation salt can be used. It is preferred that about 0.5 to about 2 equivalents of organic cation salt be used, more preferable about 1.0 to about 1.5 equivalents. It is often desirable, but not required, to remove most of the metal cation salt and most of the excess organic cation salt by washing and by other techniques known in the art. The particle size of the organoclay is reduced in size by methods known in the art, including, but not limited to, grinding, pulverizing, hammer milling, jet milling, and their combinations. It is preferred that the average particle size be reduced to less than about 100 microns in diameter, more preferably less than about 50 microns in diameter, and most preferably less than about 20 microns in diameter.

It should be appreciated that on a total composition basis dispersing aids and/or pretreatment compounds which are used may account for significant amount of the total composition, in some cases up to about 30 weight percent. While it is preferred to use as little dispersing aids and/or pretreatment compounds as possible, the amounts of dispersing aids and/or pretreatment compounds may be as much as about 10 times the amount of the platelet particles.

Oxygen Scavenging Systems

According to a preferred embodiment of this invention, the polyamide comprises a sufficient amount of an oxygen scavenging system to impart the desired oxygen barrier and scavenging effect. Because the silicate particles provide improved passive barrier to gas, oxygen scavenging by the compositions in this invention are more efficient, thus the amount of oxygen scavenging system is less than would be required in the absence of the silicate material. This feature provides the advantages of lower cost, improved ease of preparation, and improved

recyclability. The amount of oxygen scavenging system required depends on several factors, including the desired oxygen barrier, the thickness of the container or film, the amount and selection of polyamide, the amount and selection of silicate material, and the selection of oxygen scavenging system. Suitable oxygen
 5 scavenging systems comprise one or more oxidizable materials and often one or more catalysts to facilitate the oxidation reaction.

Numerous oxygen scavenging systems are known and can be incorporated into the composition of this invention. Possible oxygen scavenging systems that can be used as a component of the present invention are: ethylenically unsaturated
 10 hydrocarbons and a transition metal catalyst; ascorbate; isoascorbate; sulfite; ascorbate with a catalyst, which may be a metal, a salt, or a compound, chelate or complex of a transition metal; a transition metal complex or chelate of a polycarboxylic acid, polyamine or salicylic acid, a reduced form of a quinone, anthraquinone or other photoreducible dye, or a carbonyl compound with an
 15 absorbance in the ultraviolet spectrum ; tannin; polyethers with a transition metal catalyst; polyamides (such as, but not limited to those used to form the nanocomposite) with a transition metal catalyst; organic compounds having a tertiary hydrogen, benzylic hydrogen or allylic hydrogen in combination with a transition metal catalyst; an oxidizable metal usually in combination with a salt; or
 20 a metal in a low oxidation state that can be oxidized further to higher oxidation state, usually in combination with a salt.

Ethylenically unsaturated hydrocarbons may be any aliphatic hydrocarbon having at least one carbon-carbon double bond. These unsaturated hydrocarbons may be monomeric or polymeric compounds. Specific examples of polymeric
 25 ethylenically unsaturated compounds are polybutadienes, polystyrene-polybutadiene copolymers, polymers containing cyclohexene units, as well as polyesters, polyamides, co-polyesters and co-polyamides containing monomers having aliphatic carbon-carbon double bonds. Useful polyethers are, but are not limited to, polyethylene oxide, polypropylene oxide, polytetramethylene glycol
 30 and poly butylene oxide (poly-tetrahydrofuran). Oxidizable metals include, but are

not limited to, Fe, Co, Cu, Ni, V, Mn, Al, Zn, Si, Sn, Ti, Mg, Na. Iron(II) compounds are an example of metal compounds with a metal in a low oxidation state that can be oxidized further.

When a catalyst is used with the polyamide of the nanocomposite, a wide
 5 range of oxygen scavenging catalysts have been found to be operative, and any of these may be used in the practice of this embodiment of the present invention. Suitable oxidation catalysts include transition metal catalysts which can readily interconvert between at least two oxidation states. Preferably, the transition metal is in the form of a transition metal salt with the metal selected from the first, second
 10 or third transition series of the Periodic Table. Suitable metals include, but are not limited to Fe, Co, Cu, Ni, V, Mn, Al, Zn, Si, Sn, Ti, Mg, Na, and more specifically include manganese II or III, iron II or III, cobalt II or III, nickel II or III, copper I or II, rhodium II, III or IV and ruthenium. In some embodiments the most preferred transition metal is cobalt.

15 Suitable counterions for the metal include, but are not limited to, chloride, acetate, acetylacetonate, stearate, palmitate, 2-ethylhexanoate, neodecanoate or naphthenate. The metal salt may also be an ionomer, in which case a polymeric counterion is employed. Such ionomers are well known in the art. Any amount of catalyst which is effective in catalyzing oxygen scavenging may be used. Ranges
 20 for the oxygen scavenging catalyst include from at least about 1 ppm, preferably about 10 to about 10,000 ppm, preferably from about 50 to 500 ppm, and are readily ascertained by those skilled in the art.

The oxygen scavenging catalyst may be incorporated in a number of different ways. For example, the catalyst may be incorporated into the polyamide
 25 either before or after incorporation of the organoclay by well known methods such as admixing either before or after the formation of the polyamide pellets. The oxygen scavenging catalyst may also be incorporated into the organoclay via ion exchange, for example. Binding the oxygen scavenging catalyst to the organoclay prevents migration of the oxygen scavenging catalyst from the container wall to its
 30 contents. Moreover, the catalyst counterion is washed away during the ion

exchange process, removing another potentially undesirable migratory compound. Finally, incorporating the oxygen scavenging catalyst onto the organoclay can also provide processing benefits. It can be difficult to consistently add small amounts of a material into a polymer, such as polyamide, and to insure it has been uniformly dispersed throughout. It is also difficult to get the oxygen scavenging catalyst in a form which is soluble in the polymer melt. Crystals and particulates can be highly undesirable because they frequently impart haze and voids in the finished article.

However, when the oxygen scavenging catalyst is incorporated into the organoclay these problems are avoided. First, ion exchange allows the catalyst to be added in a soluble form. Second, far more catalyst can be added because the organoclay will be let down at the appropriate concentration into the polyamide. Finally, the concentration of the oxygen scavenging catalyst incorporated can be readily controlled by controlling the amount of clay sites available for exchange, via, for example, controlling the amount of organic cation added to the clay. Finally, because the counterion on the oxygen scavenging catalyst is washed away during the exchange process, and the oxygen scavenging catalyst is bound to the organoclay, potential migratory compounds are minimized.

An oxygen scavenging catalyst, as used in the specification and concluding claims, includes both the transition metal and counterion, and the transition metal moiety that is the resulting product a particular reaction scheme or subsequent formulation or chemical product. Thus, for example, oxygen scavenging catalyst includes both transition metals bound to counterions and the transition metal which is which are bound to other components, such as an organoclay.

Polyamides

Suitable polyamides include partially aromatic polyamides, aliphatic polyamides, wholly aromatic polyamides and mixtures and copolymers thereof. By "partially aromatic polyamide" it is meant that the amide linkage of the partially aromatic polyamide contains at least one aromatic ring and a nonaromatic species.

Suitable polyamides have a film forming molecular weight and preferably an I.V. of about 0.25 to about 1.5 dL/g, preferably about 0.4 to about 1.2 dL/g, and more preferably of about 0.7 to about 0.9 dL/g. The I.V. is measured at 25°C in a 60/40 by weight mixture in phenol/1,1,2,2-tetrachloroethane at a concentration of 0.5 grams per 100 ml. Wholly aromatic polyamides comprise in the molecule chain at least 70 mole% of structural units derived from *m*-xylylene diamine or a xylylene diamine mixture comprising *m*-xylylene diamine and up to 30% of *p*-xylylene diamine and an $\alpha\epsilon$ -aliphatic dicarboxylic acid having 6 to 10 carbon atoms, which are further described in Japanese Patent Publications No. 1156/75, No. 5751/75, No. 5735/75 and No. 10196/75 and Japanese Patent Application Laid-Open Specification No. 29697/75, the disclosure of which is incorporated herein by reference.

Polyamides formed from isophthalic acid, terephthalic acid, cyclohexanedicarboxylic acid, *meta*- or *para*-xylylene diamine, 1,3- or 1,4-cyclohexane(bis)methylamine, aliphatic diacids with 6 to 12 carbon atoms, aliphatic amino acids or lactams with 6 to 12 carbon atoms, aliphatic diamines with 4 to 12 carbon atoms, and other generally known polyamide forming diacids and diamines can be used. The low molecular weight polyamides may also contain small amounts of trifunctional or tetrafunctional comonomers such as trimellitic anhydride, pyromellitic dianhydride, or other polyamide forming polyacids and polyamines known in the art.

Preferred partially aromatic polyamides include: poly(*m*-xylylene adipamide), poly(*m*-xylylene adipamide-co-isophthalamide), poly(hexamethylene isophthalamide), poly(hexamethylene isophthalamide-co-terephthalamide), poly(hexamethylene adipamide-co-isophthalamide), poly(hexamethylene adipamide-co-terephthalamide), poly(hexamethylene isophthalamide-co-terephthalamide) and the like or mixtures thereof. More preferred partially aromatic polyamides include, but are not limited to poly(*m*-xylylene adipamide), poly(hexamethylene isophthalamide-co-terephthalamide), poly(*m*-xylylene adipamide-co-isophthalamide), and mixtures thereof. The most preferred partially

aromatic polyamide is poly(*m*-xylylene adipamide), which is available from Mitsubishi Gas and Chemical Company, Chiyodaku, Tokyo, Japan. Poly(*m*-xylylene adipamide) is a preferred polyamide due to its availability, high gas barrier properties, and processability in conjunction with PET.

5 Suitable aliphatic polyamides include polycapramide (nylon 6), poly-aminoheptanoic acid (nylon 7), poly-aminonanoic acid (nylon 9), polyundecane-amide (nylon 11), polylaurylactam (nylon 12), polyethylene-adipamide (nylon 2,6), polytetramethylene-adipamide (nylon 4,6), polyhexamethylene-adipamide (nylon 6,6), polyhexamethylene-sebacamide (nylon 10 6,10), polyhexamethylene-dodecamide (nylon 6,12), polyoctamethylene-adipamide (nylon 8,6), polydecamethylene-adipamide (nylon 10,6), polydodecamethylene-adipamide (nylon 12,6) and polydodecamethylene-sebacamide (nylon 12,8).

 Preferred aliphatic polyamides include poly(hexamethylene adipamide) and poly(caprolactam). The most preferred aliphatic polyamide is poly(hexamethylene 15 adipamide). Partially aromatic polyamides, are preferred over the aliphatic polyamides where good thermal properties are crucial.

 The most preferred polyamides include poly(*m*-xylylene adipamide), polycapramide (nylon 6), polyhexamethylene-adipamide (nylon 6,6).

 The polyamides are generally prepared by processes which are well known 20 in the art.

 The polymers of the present invention may also include suitable additives normally used in polymers. Such additives may be employed in conventional amounts and may be added directly to the reaction forming the matrix polymer. Illustrative of such additives known in the art are colorants, pigments, carbon black, 25 glass fibers, fillers, impact modifiers, antioxidants, stabilizers, flame retardants, reheal aids, crystallization aids, acetaldehyde reducing compounds, recycling release aids, plasticizers, nucleators, mold release agents, compatibilizers, processing aids and the like, or their combinations.

 All of these additives and many others and their use are known in the art 30 and do not require extensive discussion. Therefore, only a limited number will be

referred to, it being understood that any of these compounds can be used in any combination so long as they do not hinder the present invention from accomplishing its objects.

5 Processes

10 In one embodiment of this invention, a polyamide-platelet particle composite is prepared and then at least one oxygen scavenging catalyst is incorporated into the polymer-platelet particle composite. Many processes to prepare polyamide-platelet particle compositions are known, and any of these processes may be used to prepare the composites of this present invention. Although any melt mixing device may be used, typically, the melt mixing step is conducted either by a batch mixing process or by a melt compounding extrusion process during which treated or untreated layered particles are introduced into a polyamide. Use of extrusion compounding to mix the clay and the polymer is preferred because of the ease of preparation and the potential to attain high clay loadings. Prior to melt mixing, the treated or untreated layered particles may exist in various forms including pellets, flakes, chips and powder. It is preferred that the treated or untreated layered particles be reduced in size by methods known in the art, such as hammer milling and jet milling. Prior to melt mixing, the polyamide may exist in wide variety of forms including pellets, ground chips, powder and polyamide melt. In one method of preparing the polymer-platelet composites of this invention oligomeric polymers are used as the expanding agent. The clay is let down in the oligomeric material to form a concentrate, and then the concentrate is let down into the desired matrix polymer. Alternatively the oligomeric polymer and organoclay are incorporated into the polymer matrix at the same stage. Many processes to incorporate additives, such as catalysts, are known, and any of these processes may be used to prepare the composites of this present invention. In one embodiment, a concentrate of oxygen scavenging catalyst in a polyamide or copolymer or oligomer and this concentrate is mixed with the polyamide platelet particle composite.

In another embodiment, the melt mixing step is achieved by dry mixing polyamide, concentrate of platelet particles, and concentrate of oxygen scavenging catalyst then passing the mixture through a compounding extruder under conditions sufficient to melt the polyamide. In yet another embodiment of this invention, the
 5 melt mixing step is conducted by feeding the polyamide, concentrate of platelet particles, and concentrate of oxygen scavenging catalyst separately into a compounding extruder.

In a preferred embodiment of this invention, a copolymer or oligomer is melt mixed with the treated clay and oxygen scavenging catalyst to form a
 10 concentrate that is then melt mixed with a polyamide. This process can be conducted in two separate steps in which the concentrate is isolated as a solid, or in a series of two steps in which the concentrate is used as a melt mixture, or in a single step in which the components are added either simultaneously or sequentially.

In yet another embodiment the oxygen scavenging catalyst is mixed with the layered silicate material and organic cation to bind the organic cation and oxygen scavenging catalyst to said layered silicate material to form an organoclay. The organoclay is incorporated into the matrix polymer to form the polymer-platelet particle composite. This process is particularly advantageous when low
 15 extractables are desired, as the catalyst is bound to the platelet particles. Moreover, the counter ions from the cation are washed away during the exchange process, reducing the amount and type of unwanted species in the resultant polymer composite. Further, exchanging the catalyst to the platelet particles also increases the solubility of the selected oxygen scavenging catalyst in the selected polymer.
 20 This prevents, or at least minimizes, the formation of undesirable salt crystals which can degrade clarity as well as barrier in the finished article.

If desired the composites may be treated before, during or after the preparation of the composites of this invention for the purposes of increasing the molecular weight or incorporating other fillers, additives, and reagents. Increasing
 25 the molecular weight of the polyamide-platelet particle composite may be achieved

by several different methods including, but not limited to, reactive chain extension, solid state polymerization, crosslinking, and melt compounding with a high molecular weight, melt processible polyamide. Useful additives and reagents include adhesive modifiers, toners, dyes, coloring agents, UV absorbers, mold
5 release agents, impact modifiers, and their combinations.

In one embodiment of this invention, the oxygen scavenging catalyst is added to the clay either before, during, or after treatments for improving dispersion, such as treatment with organic cations. In a preferred embodiment of this process, the oxygen scavenging catalyst is incorporated onto the clay in a manner that
10 permits it to be bound to the surface of the clay. Many such processes to bind the catalyst to clay, such as by cation exchange, are known by those skilled in the art and may be used in the practice of this invention.

If desired, the oxygen scavenging polyamide platelet particle composite of this invention can be mixed with PET and related copolymers, either virgin or post
15 consumer recycled. In one embodiment of this invention, a composite is formed from a low molecular weight polyamide, silicate material, and an oxygen scavenging catalyst, then the composite is mixed with PET and related copolymers, either virgin or post consumer recycled. Use of a low molecular weight polyamide provides the advantages of improved dispersion of the high concentrations of the
20 silicate material in the polyamide composite, as well as improved mixing with the oxygen scavenging catalyst and PET.

Depending upon the polymers selected the layered silicate material may be added to a different polymer matrix than the oxygen scavenging system. For example, the layered silicate material may be added to a polyamide matrix and the
25 oxygen scavenging system may be incorporated into a polyester. These two materials could then be used to form a multilayer article, preferably with the polyester/oxygen scavenging material disposed in a layer which is closer to the packaging contents than the layer comprising the nanocomposite material.

Molded Articles

This invention also relates to articles prepared from the compositions of this invention, including, but not limited to film, sheet, molded articles, thermoformed articles, stretch blow molded containers, injection blow molded containers, and
5 extrusion blow molded containers. Molded articles typically comprise less than about 8 weight % of polyamide, preferably less than about 4 weight % of polyamide, although portions of the molded container, such as a bottle sidewall, may contain significantly higher local concentrations of the polyamide. Molded articles typically comprise less than about 2.5 weight % silicate material as
10 determined by measuring the amount of ash of the molded article when treated in accordance with ASTM D5630-94, although portions of the molded container, such as a bottle sidewall, may contain significantly higher local concentrations of the silicate material.

In an embodiment of this invention the high barrier polymer-platelet
15 particle composites is used with other polymers layers to form multilayer articles, such as, but not limited to packaging materials. By using a discrete layer of the composite, the amount of this material that is needed to generate a specific barrier level in the end application is greatly reduced, which improves recyclability and reduces cost. With the polymer-platelet particle composite being sandwiched
20 between two outer polymer layers, the surface roughness is often considerably less than for a monolayer nanocomposite material, thus reducing the level of haze. The layers of the multilayer article may be formed at the same time by co-injection molding or co-extruding or may be formed sequentially. Preferably the layers are formed in the same stage, such as by co-injection or co-extrusion.

25 In another embodiment of this invention, a mixture of PET and related copolymers, either virgin or post consumer recycled, and the polymer-platelet particle composite are used as a single layer. By using a single layer, conventional equipment for making single layer articles, film, containers, and bottles can be used without detracting significantly from the high barrier properties. If desired, the
30 mixture may be used in conjunction with one or more layers of unmodified PET for

the purposes of providing a functional barrier to the composite and/or for improving the surface finish of the product.

Examples

- 5 Oxygen consumption was measured on film samples, which were cut into strips, using a Columbus Instruments Micro-Oxymax respirometer with version 6.04b software. Samples were placed into a glass media bottle with a nominal volume of 250 ml. One empty bottle was included as a control blank. The bottles were attached to a ten port expansion module. Readings were taken at the start of
- 10 the experiment and then every four hours. The instrument measured the change in the oxygen concentration from the previous reading in each cell and calculated the total oxygen consumption and rate based on the (previously measured) volume of the cell plus oxygen sensor system. The oxygen sensor is an electrochemical fuel cell.
- 15 Carbon dioxide permeability was measured on film samples using a Mocon Oxtran 1000 permeability analyzer.

Comparative Example 1

- 20 Two trilayer films were extruded comprising internal layers of about 10 and 30 vol% of unmodified MXD6 6007, available from Mitsubishi Gas Company, with two external layers of PET-9921, available from Eastman Chemical Company. Several 2-inch square sections of the trilayer films were stretched using a T. M. Long instrument (4x4 orientation at about 110°C). The carbon dioxide permeability values of the oriented films were determined to be 174 and 59
- 25 cc•mil/100in²•day•atm, for the 10 and 30 vol% films respectively.

Comparative Example 2

- 30 Into a 34/45, single-neck, 1-liter, round-bottom flask was charged 250 grams of a low molecular weight, amine terminated poly(m-xylylene adipamide), with IV of about 0.44 dL/g, and 4.23 grams of cobalt acetate tetrahydrate. Under

nitrogen atmosphere, the mixture was heated with stirring at 250°C for 120 minutes then cooled. The material was removed from the flask, ground to pass a 3 mm screen, then stored in a nitrogen atmosphere. X-ray analysis of the product showed the concentration of cobalt in the product to be about 4000 ppm.

5 Using a Leistritz Micro-18 twin screw extruder, 10 parts of the product was extrusion compounded with 90 parts of MXD6 6007, available from Mitsubishi Gas Company, at a temperature of about 250°C with screw speed of about 260 rpm and feed rate of about 2 kg/hr, to give pelletized material with a cobalt concentration about 400 ppm. The pellets were stored under nitrogen.

10 Two trilayer films were extruded comprising internal layers of about 10 and 30 vol% of unmodified MXD6 6007, available from Mitsubishi Gas Company, with two external layers of PET-9921, available from Eastman Chemical Company. Several 2-inch square sections of the trilayer films were stretched using a T. M. Long instrument (4x4 orientation at about 110°C). The carbon dioxide permeability values of the oriented films were determined to be 168 and 54 cc•mil/100in²•day•atm, for the 10 and 30 vol% films respectively. Oxygen consumption for 3.0 grams of the inner nanocomposite layer, after removing the PET 9921 layers from the unoriented film comprising 30 vol% nanocomposite, was determined to be about 370 microliters of oxygen over a period of 136 hours, as shown in Figure 1.

20 This comparative example shows that the carbon dioxide permeability of the oxygen scavenging MXD6 is essentially equivalent to that of unmodified MXD6.

25 Example 1

 Into a 34/45, single-neck, 1-liter, round-bottom flask were charged 215.75 grams of a low molecular weight, amine terminated poly(m-xylylene adipamide), with IV of about 0.44 dL/g, 34.25 grams of organo montmorillonite clay containing a tether, octadecyl methyl bis(hydroxyethyl) ammonium chloride, an organoclay available from Southern Clay Products, and 4.23 grams of cobalt(II) acetate

tetrahydrate. Under nitrogen atmosphere, the mixture was heated with stirring at 250°C for 120 minutes then cooled. The material was removed from the flask, ground to pass a 3 mm screen, then stored in a nitrogen atmosphere. X-ray analysis of the product showed the concentration of cobalt in the product to be about 3800 ppm.

Using a Leistritz Micro-18 twin screw extruder, 10 parts of the product was extrusion compounded with 90 parts of MXD6 6007, available from Mitsubishi Gas Company, at a temperature of about 260°C with screw speed of about 250 rpm and feed rate of about 2 kg/hr, to give pelletized material with a cobalt concentration of about 400 ppm and silicate concentration (ash) of about 1.0 wt%. The pellets were stored under nitrogen.

Two trilayer films were extruded comprising internal layers of about 10 and 30 vol% of unmodified MXD6 6007, available from Mitsubishi Gas Company, with two external layers of PET-9921, available from Eastman Chemical Company. Several 2-inch square sections of the trilayer films were stretched using a T. M. Long instrument (4x4 orientation at about 110°C). The carbon dioxide permeability values of the oriented films were determined to be 117 and 41 cc•mil/100in²•day•atm, for the 10 and 30 vol% films respectively. Oxygen consumption for 3.0 grams of the inner nanocomposite layer, after removing the PET 9921 layers from the unoriented film comprising 30 vol% nanocomposite, was determined to be about 680 microliters of oxygen over a period of 136 hours, as shown in Figure 1.

This example shows that the nanocomposite composition of this invention has significantly improved carbon dioxide barrier and oxygen consumption.

Comparative Example 3

Using a Leistritz Micro-18 twin screw extruder, 4 parts of the material prepared in Comparative Example 1 was extrusion compounded with 96 parts of PET-20261, available from Eastman Chemical Company, at a temperature of about 275°C with screw speed of about 300 rpm and feed rate of about 2 kg/hr, and the

composite was stored under nitrogen. A trilayer film was extruded comprising internal layers of about 50 vol% of this material with two external layers of PET-9921, available from Eastman Chemical Company. Several 2-inch square sections of the trilayer film was stretched using a T. M. Long instrument (4x4 orientation at about 110°C). The carbon dioxide permeability value of the oriented film was determined to be 411 cc-mil/100 in²-24hr.-atm, for the 50 vol% film. Oxygen consumption for 10 grams of the unoriented film comprising 50 vol% of the blend of PET 9921 with the nanocomposite was determined to be about 60 microliters of oxygen over a period of 136 hours, as shown in Figure 2.

Example 2

Using a Leistritz Micro-18 twin screw extruder, 4 parts of the composite prepared in Example 1 was extrusion compounded with 96 parts of amber PET-20261, available from Eastman Chemical Company, at a temperature of about 275°C with screw speed of about 300 rpm and feed rate of about 2 kg/hr, and the composite was stored under nitrogen.

Two trilayer films were extruded comprising internal layers of about 30 and 50 vol% of this material with two external layers of PET-9921, available from Eastman Chemical Company. Several 2-inch square sections of the trilayer films were stretched using a T. M. Long instrument (4x4 orientation at about 110°C). The carbon dioxide permeability values of the oriented films were determined on a Mocon Oxtran 1000 permeability tester to be 317 and 291 cc•mil/100in²•day•atm, for the 30 and 50 vol% films respectively. Oxygen consumption for 10 grams of the unoriented film comprising 50 vol% of the blend of PET 9921 with the nanocomposite was determined to be about 60 microliters of oxygen over a period of 136 hours, as shown in Figure 2.

This example shows that the improvements are obtained even when very minor amounts of the composite of this invention are used as a blend in PET.

Example 3

This example illustrates the preparation of montmorillonite clay in which 50% of the sodium cations are exchanged with cobalt and 50% with protons. 40 g (38.0 meq of exchangeable sodium) of refined Wyoming type sodium montmorillonite with cation exchange capacity of 0.95 meq/ g available from Southern Clay Products was dispersed in 2000 ml of 70°C water in a Commercial Waring Blender. Then 2.36 g (19 meq) of cobalt(II) acetate tetrahydrate in 200 ml of water was added followed by additional blending. 50 ml of 0.962 N HCl was then added. The mixture was blended, centrifuged, washed with 1000 ml of water in the blender, then centrifuged again. The product was dried in an oven at 60°C overnight to provide 14.3 g of final product. Ash content was 87.15 wt %, cobalt content was 1.23 %, and X-ray basal spacing was 1.25 nm.

13.2 grams of the treated clay, prepared as described above, was dry mixed with 269 parts of a low molecular weight poly(m-xylylene adipamide), with IV of about 0.41 dL/g. The mixture was dried at 110°C overnight in a vacuum oven then extruded on the Leistritz Micro 18 extruder equipped with a general compounding screw. The AccuRate pellet feeder was set at a rate of approximately 2 kg/hr with a nitrogen atmosphere over both the feeder and the hopper. The barrel zones were set at 230°C (zone 2), 240°C (zones 3-5), 245°C (zones 6-7) and 250°C (zone 8 and die) with the screw RPM at approximately 275.

This material showed good oxygen consumption.

Example 4

This example illustrates the preparation of montmorillonite clay in which 50 % of the sodium cations are exchanged with cobalt(II), 25% with octadecyltrimethylammonium cations, and 25 % with protons. 10 g (9.5 meq of exchangeable sodium) of refined Wyoming type sodium montmorillonite with cation exchange capacity of 0.95 meq/ g available from Southern Clay Products was dispersed in 500 ml of 70°C water in a Waring blender. Then 0.59 g (4.75 meq) of cobalt(II) acetate tetrahydrate and 1.64 g (2.375 meq) of

octadecyltrimethylammonium chloride (commercially available as Arquad 18-50 from Akzo Nobel) in 50 ml of water was added followed by additional blending. 5 ml of 0.962 N HCl was then added. The mixture was blended, centrifuged, washed with 250 ml of water in the blender, then centrifuged again. The product was dried
 5 in an oven at 60°C overnight to provide 6.64 g of final product. Cobalt content was 0.99 %, and X-ray basal spacing was 1.34 nm.

13.4 grams of the treated clay, prepared as described above, was dry mixed with 270 parts of a low molecular weight poly(m-xylylene adipamide), with IV of about 0.41 dL/g. The mixture was dried at 110°C overnight in a vacuum oven then
 10 extruded on the Leistritz Micro 18 extruder equipped with a general compounding screw. The AccuRate pellet feeder was set at a rate of approximately 2 kg/hr with a nitrogen atmosphere over both the feeder and the hopper. The barrel zones were set at 230°C (zone 2), 240°C (zones 3-5), 245°C (zones 6-7) and 250°C (zone 8 and die) with the screw RPM at approximately 275.

15 This material showed good oxygen consumption.

Example 5

This example illustrates the preparation of montmorillonite clay in which 50 % of the sodium cations are exchanged with cobalt(II) and 50% with
 20 octadecyl,trimethyl ammonium cations. 10 g (9.5 meq of exchangeable sodium) of refined Wyoming type sodium montmorillonite, with cation exchange capacity of 0.95 meq/g and available from Southern Clay Products, is dispersed in 500 ml of 70°C water in a Waring Blender. Then 0.59 g (4.75 meq) of cobalt(II) acetate tetrahydrate and 3.28 g (4.75 meq) of octadecyltrimethyl ammonium chloride
 25 (commercially available as Arquad 18-50 from Akzo Nobel) in 50 ml of water is added. The mixture is blended, centrifuged, washed with 250 ml of water in the blender, then centrifuged again. The product is dried in an oven at 60°C overnight.

5 parts of the treated clay, prepared as described above, is dry mixed with 95 parts of a low molecular weight poly(m-xylylene adipamide), with IV of about
 30 0.41 dL/g. The mixture is dried at about 110°C overnight in a vacuum oven then

extruded on the Leistritz Micro 18 extruder equipped with a general compounding screw at a temperature of about 260°C.

This material showed good oxygen consumption.

5 Example 6

547 parts of a low molecular weight poly(m-xylylene adipamide) with IV of about 0.44 dL/g, 129 parts of organo montmorillonite clay containing a tether, octadecyl methyl bis(hydroxyethyl) ammonium chloride, an organoclay available from Southern Clay Products, and 39.8 parts of cobalt(II) acetate tetrahydrate were
10 dry mixed then dried at 80°C overnight in a vacuum oven. The mixture was then extruded on the Leistritz Micro 18 corotating twin screw extruder equipped with a general compounding screw at a temperature of about 260°C, with screw speed of about 250 rpm, and a feed rate of about 2 kg/hr. The material was air-cooled on a casting belt then pelletized upon exiting the extruder. After the extrusion was
15 complete, about 40 parts of the pellets were dry-mixed with about 960 parts of CB11, a polyester available from Eastman Chemical Company. The mixture was then extruded on the Leistritz extruder at a temperature of about 280°C, with screw speed of about 250 rpm, and a feed rate of about 2 kg/hr. The material was extruded into 5-mil thick film. This film exhibited good carbon dioxide barrier and
20 oxygen consumption.

Example 7

The procedure of Example 6 was repeated except that 547 parts of the low molecular weight nylon, 263 parts of organo montmorillonite clay containing a
25 tether, octadecyl methyl bis(hydroxyethyl) ammonium chloride, an organoclay available from Southern Clay Products, and 40.6 parts of cobalt(II) acetate tetrahydrate in the first extrusion.

Comparative Example 4

The procedure of Example 6 was repeated except that no oxygen scavenging catalyst was used.

5 Comparative Example 5

The procedure of Example 7 was repeated except that no oxygen scavenging catalyst was used.

CLAIMS

WE CLAIM:

- 5 1. A polymer-platelet particle composite comprising at least one polyamide, at least one oxygen scavenging system, and platelet particles derived from at least one layered silicate material.
2. The composition of claim 1 wherein said polyamide resin is selected from the group consisting of partially aromatic polyamides.
- 10 3. The composition of claim 1 wherein said polyamide resin is selected from the group consisting of poly(m-xylylene adipamide), poly(hexamethylene isophthalamide-co-terephthalamide), poly(m-xylylene adipamide-co-isophthalamide), and mixtures thereof.
4. The composition of claim 1 wherein said polyamide resin comprises
15 poly(m-xylylene adipamide).
5. The composition of claim 1 wherein said platelet particles are present in an amount up to about 30 weight percent.
6. The composition of claim 1 wherein said platelet particles are present in an amount up to about 20 weight percent.
- 20 7. The composition of claim 1 wherein said platelet particles are present in an amount between about 0.01 weight percent and about 20 weight percent.
8. The composition of claim 1 wherein said platelet particles are present in an amount between about 0.5 weight percent and about 20 weight percent.
9. The composition of claim 1 wherein said layered silicate material
25 comprises sodium bentonite, sodium montmorillonite or mixtures thereof.
10. The composition of claim 1 wherein said oxygen scavenging system comprises an oxygen scavenging catalyst which comprises at least one transition metal compound.
11. The composition of claim 10 wherein said oxygen scavenging catalyst is
30 selected from the group consisting of the first, second, and third transition series.

12. The composition of claim 10 wherein said oxygen scavenging catalyst which comprises at least one cobalt compound.

13. The composition of claim 11 wherein said cobalt compound is selected from the group consisting of organic acids, acetates, halides, and mixtures thereof.

5 14. The composition of claim 1 wherein said oxygen scavenging system is selected from the group consisting of ethylenically unsaturated hydrocarbons and a transition metal catalyst; ascorbate; isoascorbate; sulfite; ascorbate with an oxygen scavenging catalyst; transition metal complex or chelate of a polycarboxylic acid; transition metal complex or chelate of polyamine; transition metal complex or
10 chelate of salicylic acid; a reduced form of a photoreducible dye compound; carbonyl compound with an absorbance in the ultraviolet spectrum; tannin; polyethers with a transition metal catalyst; polyamides with a transition metal catalyst; organic compounds having a tertiary hydrogen, benzylic hydrogen or allylic hydrogen in combination with a transition metal catalyst; an oxidizable
15 metal in combination with a salt; or a metal in a low oxidation state that can be oxidized further to higher oxidation state, usually in combination with a salt.

15. The composition of claim 14 wherein said photoreducible dye is selected from the group consisting of quinones and anthraquinones

16. The composition of claim 1 wherein said layered silicate material is a Wyoming-type sodium montmorillonite or Wyoming-type sodium bentonite which has been treated with one or more alkoxylated ammonium cations.

17. The composition of claim 1 further comprising at least one antioxidant.

20 18. The composition of claim 1 further comprising at least one photoinitiator.

19. An article comprising at least a first and a second layer, said first layer comprising a polyamide having dispersed therein at least one layered silicate material and wherein said second layer comprises a polymer and an oxygen
25 scavenging system.

20. The article of claim 19 wherein said layered silicate material comprises a Wyoming-type sodium montmorillonite or Wyoming-type sodium bentonite

which has been treated with one or more alkoxyated ammonium cations; wherein said polymer comprises a polyester and said oxygen scavenging system comprises at least one polyether compound and at least one oxygen scavenging catalyst.

21. The article of claim 19 wherein said polymer comprises polyethylene methyl acrylate and said oxygen scavenging system comprises a transition metal catalyst and a cyclohexene moiety copolymerized onto said polymer.

22. The article of claim 19 wherein said article is a container or a preform comprising at least three layers in at least a portion of said article.

23. The article of claim 19 wherein said oxygen scavenging composition is blended with recycled polyester.

24. A multilayer article wherein at least one layer comprises the composition of claim 1.

25. The article of claim 24 wherein said at least one layer is disposed between a first and third layer each of which comprises at least one polyester.

26. The article of claim 24 wherein said article is selected from the group consisting of film, sheet, tubing, profiles, pipes, fiber, containers, preforms, thermoformed articles and flexible bags.

27. The article of claim 24 wherein said article is a container or a preform comprising at least three layers in at least a portion of said article.

28. The article of claim 24 wherein said article is a container or a preform comprising at least four layers in at least a portion of said article.

29. The article of claim 24 wherein said polymer-platelet particle composite is disposed in an intermediate layer between a first and fourth layer each of which comprises at least one polyester.

Abstract

The present invention relates to polymer-platelet particle composites comprising at least one polyamide resin, at least one oxygen scavenging system, and platelet particles derived from at least one layered silicate material.

5

10

n:\docket\71111\comp appln doc

15




Fig. 1




Fig. 2

Please type a plus (+) sign in this box →

+

DECLARATION FOR UTILITY OR DESIGN PATENT APPLICATION

☐ Declaration Submitted with Initial Filing OR ☐ Declaration Submitted after Initial Filing

Attorney Docket Number 71111

First Named Inventor Linda Gail Bernard

COMPLETE IF KNOWN

Application Number

Filing Date 08/02/2000

Group Art Unit

Examiner Name

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

POLYAMIDE NANOCOMPOSITES WITH OXYGEN SCAVENGING CAPABILITY

(Title of Invention)

the specification of which

☒ is attached hereto

OR

☐ was filed on (MM/DD/YYYY)

as United States Application Number or PCT International

Application Number

and was amended on (MM/DD/YYYY)

(if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment specifically referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37 Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code § 119 (a)-(d) or § 365 (b) of any foreign application(s) for patent or inventor's certificate, or § 365 (a) of any PCT international application which designated at least one country other than the United States of America, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or of any PCT international application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application Number(s)	Country	Foreign Filing Date (MM/DD/YYYY)	Priority Not Claimed	Certified Copy Attached?	
				Yes	No
			<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

☐ Additional foreign application numbers are listed on a supplemental priority data sheet attached hereto:

I hereby claim the benefit under Title 35, United States Code § 119(e) of any United States Provisional Application(s) listed below.

Application Number(s)	Filing Date (MM/DD/YYYY)	<input type="checkbox"/> Additional Provisional application numbers are listed on a supplemental priority data sheet attached hereto.
60/148,138	08/10/1999	
60/165,064	11/12/1999	

Please type a plus (+) sign in this box →



DECLARATION - Utility or Design Patent Application

I hereby claim the benefit under Title 35, United States Code §120 of any United States application(s), or §365(c) of any PCT international application designating the United States of America, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code §112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations §1.56 which became available between the filing date of the prior application and the national or PCT international filing date of this application.

U.S. Parent Application Number	PCT Parent Number	Parent Filing Date (MM/DD/YYYY)	Parent Patent Number (if applicable)

☐ Additional U.S. or PCT international application numbers are listed on a supplemental priority data sheet attached hereto.

As a named inventor, I hereby appoint the following registered practitioner(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

Name	Registration Number	Name	Registration Number
Rose M. Allen	35,424	Matthew W. Smith	35,366
Michael J. Blake	37,096	Cheryl J. Tubach	38,346
Betty J. Boshears	33,864	Jonathan D. Wood	39,076
Harry J. Gwinnell	29,000		
Karen A. Harding	33,967		

☐ Additional registered practitioner(s) named on supplemental Registered Practitioner Information sheet attached hereto

Direct all correspondence to:

Name	Karen A. Harding						
Address	Eastman Chemical Company						
Address	P.O. Box 511						
City	Kingsport			State	Tennessee		ZIP 37662
Country	USA		Telephone	(423) 229-4016		Fax	(423) 229-1239

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Name of Sole or First Inventor ☐ A petition has been filed for this unsigned inventor

Given Name (first and middle (if any))	Family Name or Surname
Linda Gail	Bernard

Inventor's Signature _____

Date _____

Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
------------------------------	--------------------	-------------------	-----------------------

Post Office Address

309 Castaway Drive

City Kingsport	State Tennessee	ZIP 37663-3568	Country U.S.A.
-------------------	--------------------	-------------------	-------------------

☒ Additional inventors are being named on the 3 supplemental Inventor(s) sheet(s) attached hereto.

Please type a plus (+) sign in this box → +

DECLARATION	ADDITIONAL INVENTOR(S) Supplemental Sheet
--------------------	---

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Horst		Clauberg	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship DE
Post Office Address 2601 J B Dennis #210			
City Kingsport	State Tennessee	ZIP 37660-4786	Country U.S.A.

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Michael John		Cyr	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 204 Coralwood Drive			
City Kingsport	State Tennessee	ZIP 37663-2712	Country U.S.A.

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
John Walker		Gilmer	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 2624 Wildwood Drive			
City Kingsport	State Tennessee	ZIP 37660-4754	Country U.S.A.

Please type a plus (+) sign in this box → +

DECLARATION		ADDITIONAL INVENTOR(S) Supplemental Sheet	
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
James Christopher		Matayabas, Jr.	
Inventor's Signature _____ Date _____			
Residence: City Chandler	State Arizona	Country U.S.A.	Citizenship U.S.A.
Post Office Address 1380 West Saragosa Place			
City Chandler	State Arizona	ZIP 85224-7216	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Jeffrey Todd		Owens	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 117 Willowbrook Drive			
City Kingsport	State Tennessee	ZIP 37660-7581	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Mark Edward		Stewart	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 1104 Dover Drive			
City Kingsport	State Tennessee	ZIP 37664	Country U.S.A.

Please type a plus (+) sign in this box → +

DECLARATION	ADDITIONAL INVENTOR(S) Supplemental Sheet
--------------------	---

Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Sam Richard		Turner	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 1037 Sussex Drive			
City Kingsport	State Tennessee	ZIP 37660-5836	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Shriram		Bagrodia	
Inventor's Signature _____ Date _____			
Residence: City Kingsport	State Tennessee	Country U.S.A.	Citizenship U.S.A.
Post Office Address 2649 Suffolk Street			
City Kingsport	State Tennessee	ZIP 37660-5803	Country U.S.A.
Name of Additional Joint Inventor, if any:		<input type="checkbox"/> A petition has been filed for this unsigned inventor	
Given Name (first and middle [if any])		Family Name or Surname	
Inventor's Signature _____ Date _____			
Residence: City	State	Country	Citizenship
Post Office Address			
City	State	ZIP	Country